

HDPE PE100
YUHWA HIDDEN P600

Features and Uses

Application	HDPE PE100
Features	PE100, Excellent Creep Resistance, SCG, RCP, Color:Natural
Uses	Gas Pipes, Water Supply and Drain Pipes

Properties

Items	Specification	Unit	Test Method
Melt Index (5kg)	0.22	g/10min.	ASTMD1238
Density	0.952	g/cm ³	ASTMD1505
Water Absorption	<0.01	%	ASTMD570
Tensile Strength at Yield	230	kgf/cm ²	ASTMD638
Elongation at Break	>600	%	ASTMD638
Flexural Modulus	9,000	kgf/cm ²	ASTMD790
Hardness (Rockwell)	62	shore D	ASTMD2240
Impact Strength (Izod with Notch)	>50	kgf cm/cm	ASTMD256
Environment Stress Cracking Resistance	>5,000	hr.Cond.B.10%	ASTMD1693
Melting Point	130	°C	ASTMD3418
Softening Point (Vicat)	124	°C	ASTMD1525
Oxidation Induction Time at 200°C	>60	min	ASTMD3895
Heat Deflection Temperature	65	°C	ASTMD648
Brittleness Temperature	<-70	°C	ASTMD746

※ Above data are intended to serve as guides only, and are not sales specification limits.

Contact Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Sales PP Team	82-2-2122-1522~1527	82-2-2122-1519	H15106@kpic.co.kr