

## Data Sheet Advanced-PP 1104K

### Description

Advanced-PP 1104K is a polypropylene homopolymer with medium molecular weight distribution (MWD) and narrow MFR range. Main application is OPP core layers and high performance weaving tapes.eg for carpet backing. The product is free from metal stearates and functional additives like slip agents and is therefore in particular suitable for metallisable BOPP film and provides low water-carry over.

### Application

OPP films ( stenter frame process), weaving tapes.

### Regulatory Information:

The Grade Advanced-PP 1104K and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon request.

### Properties ( Typical values)

Properties	Unit	Test method	Value
<b>Melt Flow Rate</b>			
Melt flow rate (230°C / 2.16 KG)	g / 10 min	ISO 1133	3.2
<b>Mechanical Properties</b>			
Tensile modulus of elasticity (v= 1 mm/min)	MPa	ISO 527-2	1450
Tensile stress at yield (v= 50 mm/min)	MPa	ISO 527-2	34
Tensile strain at yield (v= 50 mm/min)	%	ISO 527-2	9
Tensile strain at break (v= 50 mm/min)	%	ISO 527-2	>50
Charpy impact strength unnotched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eU	190
Charpy impact strength notched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eA	4.0
Ball indentation hardness ( H 358/30)	MPa	ISO 2039-1	74
<b>Thermal Properties</b>			
Melting point, DSC	°C	ISO 3146	163
Heat deflection temperature- HDT/B (0.45 Mpa)	°C	ISO 75-2	85
Vicat softening temperature- VST/A50 (10 N)	°C	ISO 306	154
<b>Other Properties</b>			
Density	g / cm <sup>3</sup>	ISO 1183	0.91

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.

Jul'22

Advanced Petrochemical Company  
 Saudi Joint Stock Company

Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia  
 Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia  
 Tel: +966 13 359 1000 Fax: +966 13 356 6065 C.R. 2055008094  
 Paid up capital: S.R. 1,967,940,000.00

[www.advancedpetrochem.com](http://www.advancedpetrochem.com)

الشركة المتقدمة للبتروكيماويات  
 شركة مساهمة سعودية

المركز الرئيسي - الدمام ص.ب. ٧٢١٥ - الدمام ٣١٤٦٢ المملكة العربية السعودية  
 الجبيل ص.ب. ١١٠٢٢ - الجبيل ٣١٩٦١ المملكة العربية السعودية  
 هاتف: +٩٦٦ ١٣ ٣٥٩ ١٠٠٠ فاكس: +٩٦٦ ١٣ ٣٥٦ ٦٠٦٥ س.ت. ٢٠٥٥٠٨٠٩٤  
 رأس المال المدفوع: ١,٩٦٧,٩٤٠,٠٠٠