



# Loyal Group

## Kingpor<sup>®</sup>

### Expandable Polystyrene: Non-Fire Retardant Grade

Type	Expansion	Grades	Particle Size Range (mm)	Foam Density (g/l)	Characteristics	Principal Applications
<b>E series</b>	1 time expansion	E-MS	1.2-1.8	13-15	Low density, high strength, good fusion, beautiful surface.	Electronic appliances packaging, fishing boxes, art works packaging, sports protections, floating ball, blocks, etc.
		E-SA	0.9-1.4	14-17		
		E-SB	0.7-1.1	15-20		
		E-S	0.5-0.9	18-25		
<b>B series</b>	1 time expansion	B-MS	1.2-1.8	16-20	Short time cooling and molding, short cycle time, low energy consumption, low VOC, low density.	Electronic appliances packing, suitable for other packaging.
		B-SA	0.9-1.4	17-22		
		B-SB	0.7-1.1	18-25		
		B-S	0.5-0.9	20-30		

Type	Expansion	Grades	Particle Size Range (mm)	Foam Density (g/l)	Characteristics	Principal Applications
<b>H series</b>	1 time expansion	H-MS	1.2-1.8	11-15	Easily achieve light density and economic consumption.	Light block, often used for cutting board, lost foam casting, light packaging, etc.
		H-SA	0.9-1.4	11-15		
		H-SB	0.7-1.1	13-16		
		H-S	0.5-0.9	13-18		
	3~5 times expansion	H-MS	1.2-1.8	6-7	Easily achieve light density and economic consumption.	Light block, often used for cutting board, lost foam casting, light packaging, etc.
		H-SA	0.9-1.4	7-8		
		H-SB	0.7-1.1	8-9		
		H-S	0.5-0.9	9-10		

## Expandable Polystyrene: Fire Retardant Grade

<b>GF series</b>	1 time expansion	GF-MS	1.2-1.8	14-18	Fire retardant without HBCD.	Building insulation, also suitable for electronics structural parts.
		GF-SA	0.9-1.4	15-20		
		GF-SB	0.7-1.1	18-25		
		GF-S	0.5-0.9	20-35		
<b>GF(L) series</b>	1 time expansion	GF(L)-MS	1.2-1.8	18-25	Low pentane, low VOC for block molding and shape molding without HBCD.	Building insulation, also suitable for electronics structural parts.
		GF(L)-SA	0.9-1.4	18-30		
		GF(L)-SB	0.7-1.1	20-40		
		GF(L)-S	0.5-0.9	22-50		

Type	Expansion	Grades	Particle Size Range (mm)	Foam Density (g/l)	Characteristics	Principal Applications
<b>LR Series</b> Grey	1 time expansion	LR-1915	1.0-1.8	17-20	Grey color, low thermal conductivity. Without HBCD.	Thermal insulation, construction material, etc.
		LR-1610	0.7-1.1	18-22		
		LR-1608	0.5-0.8	25-40		
		LR -1925A	1.8-2.5	15-20		

### Extruded Polystyrene: Fire Retardant Grade

<b>XLR series</b> Grey	1 time expansion	XLR-1610	0.95-1.25	≥15	Grey color, low thermal conductivity. Without HBCD.	Thermal insulation, construction material, etc.
		XLR-1608	0.7-0.95	≥25		

### Extruded Polystyrene: Non-Fire Retardant Grade

<b>HP series</b>	1 time expansion	HP-1501	0.9-1.4	≥25	High impact resistance, high strength. Good fusion, good cushion.	Appliances, LCD, computer parts, electronic parts, etc.
------------------	------------------	---------	---------	-----	---	---

Type	Expansion	Grades	Particle Size Range (mm)	Foam Density (g/l)	Characteristics	Principal Applications
<b>XHP series</b>	1 time expansion	XHP-1501	0.9-1.4	≥25	Fast expansion, good fusion, high strength, beautiful surface, excellent impact resistance and toughness.	Car bumper, safety seat, packaging of LCD panels, etc.

**Expandable Polystyrene (Customized Grade) : Non-Fire Retardant Grade**

<b>H series</b>	1 time expansion	H-4S	0.3-0.6	18-40	Wide used in lost foam casting field due to good property of rapid evaporation, low-carbon, and high adhesion.	Exclusively used for Lost foam casting.
<b>E series</b>	1 time expansion	E-4S	0.3-0.6	20-50	Low smell and noise in pre-expansion.	Filler material: used for toys, pillows, backrest cushion, precision structural, etc.
<b>B series</b>	1 time expansion	B-4S	0.3-0.6	22-50	Low smell and noise in pre-expansion.	Filler material: used for toys, pillows, backrest cushion, precision structural, etc.

Type	Expansion	Grades	Particle Size Range (mm)	Foam Density (g/l)	Characteristics	Principal Applications
<b>G series</b>	1 time expansion	G-XXL	≥4.0	25-50	Rounded particles, high strength.	Filtration material, water-resisting layer, filling layer, etc.
		G-XL	2.80-3.60	20-50		
		G-L	2.20-2.80	20-50		
Limited Supply						

## Expandable Polystyrene (Customized Grade) : High Antistatic Grade

<b>D series</b>	1 time expansion	D-B-MS	1.2-1.8	15-20	Surface impedance value of final product is $10^9$ - $10^{11}\Omega$	High antistatic grade: suitable for antistatic packaging, such as touch screen, LCD.
		D-B-SA	0.9-1.4	18-22		
		D-B-SB	0.7-1.1	20-40		
		D-B-S	0.5-0.9	25-40		
Limited Supply						

## Packing Information

Packing	Weight	20 ft Container	40 ft Container
Paper Bag	<b>25 KG</b>	17 MT	25.5 MT
Flecon Bag	<b>750 KG</b>	15 MT	25.5 MT
	<b>850 KG</b>	17 MT	25.5 MT

## Origin Information

Type	China	Taiwan	Type	China	Taiwan
<b>E series</b>	○	○	<b>G series</b>	○	×
<b>B series</b>	○	○	<b>D series</b>	○	×
<b>H series</b>	○	○	<b>LR series</b>	○	×
<b>GF series</b>	○	○	<b>XLR series</b>	○	×
<b>GF(L) series</b>	×	○	<b>HP series</b>	○	×
-	-	-	<b>XHP series</b>	○	×

### Disclaimer

The data contained in these specifications are based on our current knowledge and experience. In the view of many factors that may affect processing and application of our product, these data do not relieve processors from obligations of carrying out own investigations and tests; and these data does not imply any warranties for certain properties, or the fitness for particular purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior notice. It is the responsibility of the recipient of our products to ensure that any obligations and existing laws and regulations are observed. We are not responsible for any direct, occasional, or indirect injury or harm caused in operation according to this document.

